

PLYWOOD FENÓLICO GRADO MARÍTIMO
USO: PISO CONTENEDORES

Dimensiones (mm)	1220 * 2440
Grosor (mm)	28
Tolerancia (mm)	± 0.5
Capas (Láminas)	21
Film	Resistente al agua
Color film	Negro
Material (madera)	Abedul
Pegamento	WBP Fenólico resistente al agua
Capacidad de fuerza	7.2 toneladas
Clasificación IICL	T7
IICL TB001	>6,780N
MOD (Módulo de rotura)	103.9 Mpa
MOE (Módulo de elasticidad)	11,872 Mpa



**...Protecting
Against Soak
Damage**

Table 1.9
T 7 - Only floor boards manufactured to pass ISO** floor strength test at 7.2 tons and above
T 6 - Only floor boards manufactured to pass ISO floor strength test at between 6.0 and 7.2 tons
T 5 - Only floor boards manufactured to pass ISO floor strength test at between 5.0 and 6.0 tons
** ISO floor test 1496 - 1 Sixth Edition 2013-07-01 – 6.9 Test No. 8

Características:

- Tablero con película fenólica impermeable IICL , ISO T7
- Láminas contrachapadas presionadas con planchas de calor
- Láminas contrachapadas pegadas con adhesivo resistente al agua
- Calidad T7

